

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Bronze](#)

Characteristics for grade BrO5S25 (БpO5C25).

Grade :	BrO5S25 (БpO5C25)
Classification :	Tin foundry bronzes
Equivalent grades:	Go here

Chemical composition in % for grade BrO5S25 (БpO5C25)

Fe	Si	P	Al	Cu	Pb	Zn	Sb	Sn	Impurity
max 0.2	max 0.02	max 0.05	max 0.02	66.8 - 73	23 - 26	max 0.5	max 0.5	4 - 6	all 1.2

Comment: Cu is a basis; the percentage of Cu is given approximately.

Mechanical properties under T=20°C for grade BrO5S25 (БpO5C25)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
cast in a metal mould, GOST 613-79			137		6			Without heat treatment
sand (mould) casting, GOST 613-79			147		5			Without heat treatment

Brinell hardness for BrO5S25 (БpO5C25) (without heat treatment) , cast in a metal mould GOST 613-79	HB 10 ⁻¹ = 60 MPa
Brinell hardness for BrO5S25 (БpO5C25) (without heat treatment) , sand (mould) casting GOST 613-79	HB 10 ⁻¹ = 45 MPa

Friction coefficient of the material BrO5S25 (БpO5C25) .

Friction coefficient with oil :	0.004
Friction coefficient without oil :	0.14

Technological properties of the material BrO5S25 (БpO5C25) .

Melting temperature :	940 °C
Casting temperature :	1150 °C
Linear shrinkage :	1.5 %

Physical properties for grade BrO5S25 (БpO5C25)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m

20	0.686	17.6	58.6			
----	-------	------	------	--	--	--

Equivalent steels for grade BrO5S25 (БpO5C25)

Warning! Indicated both exact and nearest equivalents.

USA
-
C94300

Specification :**Mechanical properties :**

- σ_B - Tensile strength , [MPa]
 σ_T - Yield stress , [MPa]
 δ_5 - Specific elongation at fracture , [%]
 ψ - Reduction of area , [%]
KCU - Impact strength , [kJ / m²]
HB - Brinell hardness , [MPa]

Physical properties :

- T** - Test temperature , [Grade]
E - Young modulus , [MPa]
 α - Coefficient of linear expansion (range 20° - T) , [1/Grade]
 λ - Thermal (heat) condition coefficient , [Watt/(m·Grade)]
 ρ - Density , [kg/m³]
C - Specific heat (range 20° - T) , [J/(kg·Grade)]
R - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).

Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

