

Database of Steel and Alloy (Marochnik)

splav.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Cast iron](#)

Characteristics for grade CHNKHMDSH (ЧНХМДШ).

Grade :	CHNKHMDSH (ЧНХМДШ)
Classification :	Low alloy cast iron
Equivalent grades:	Is absent

Chemical composition in % for grade CHNKHMDSH (ЧНХМДШ)

C	Si	Mn	Ni	S	P	Cr	Mo	Cu
3 - 3.6	2 - 2.8	max 0.6	0.6 - 1	max 0.03	max 0.08	0.2 - 0.4	0.2 - 0.6	0.5 - 0.8

Mechanical properties under T=20°C for grade CHNKHMDSH (ЧНХМДШ)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Casting, GOST 7769-82			600					

Brinell hardness for CHNKHMDSH (ЧНХМДШ) , GOST 7769-82	HB 10⁻¹ = 270 - 320 MPa
---	---

Specification :

Mechanical properties :

- σ_B - Tensile strength , [MPa]
- σ_T - Yield stress , [MPa]
- δ_5 - Specific elongation at fracture , [%]
- ψ - Reduction of area , [%]
- KCU** - Impact strength , [kJ / m²]
- HB** - Brinell hardness , [MPa]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

