

Database of Steel and Alloy (Marochnik)

splay.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Copper](#)

Characteristics for grade MNTS18-27 (MHЦ18-27).

Grade :	MNTS18-27 (MHЦ18-27)
Classification :	Copper-nickel alloys
Equivalent grades:	Go here

Chemical composition in % for grade MNTS18-27 (MHЦ18-27)

Ni+Co	Fe	Mn	Cu	Pb	Zn	Impurity
17 - 19	max 0,3	max 0,5	53 - 56	max 0,05	24,4 - 30	all 0,6

Comment: **Zn** is a basis; the percentage of **Zn** is given approximately.

Equivalent steels for grade MNTS18-27 (MHЦ18-27)

Warning! Indicated both exact and nearest equivalents.

USA	Germany	Japan
-	DIN,WNr	JIS
C77000	2.0742 CuNi18Zn27	C7701

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

