

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Copper](#)

Characteristics for grade M1f (M1ф).

Grade :	M1f (M1ф)
Classification :	Copper
Equivalent grades:	Go here

Chemical composition in % for grade M1f (M1ф)

Fe	Ni	S	P	As	Pb	Zn	Sb	Bi	Sn	-
max 0.005	max 0.002	max 0.005	0.012 - 0.04	max 0.002	max 0.005	max 0.005	max 0.002	max 0.001	max 0.002	Cu+Ag min 99.9

Mechanical properties under T=20°C for grade M1f (M1ф)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Pipe, GOST 617-2006			180-190		32			
soft cold-rolled, GOST 1173-2006			200-260		42			
hard cold-rolled, GOST 1173-2006			290		6			

Brinell hardness for M1f (M1ф) , soft GOST 1173-2006	HB 10 ⁻¹ = 55 MPa
Brinell hardness for M1f (M1ф) , hard GOST 1173-2006	HB 10 ⁻¹ = 95 MPa

Technological properties of the material M1f (M1ф) .

Melting temperature :	1083 °C
Casting temperature :	1150 - 1250 °C
Linear shrinkage :	2.1 %

Physical properties for grade M1f (M1ф)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20	1.32		387	8940	390	17.8
100	1.28	16.7				

Equivalent steels for grade M1f (M1φ)

Warning! Indicated both exact and nearest equivalents.

European
EN
Cu-DHP

Specification :**Mechanical properties :**

- σ_B - Tensile strength , [MPa]
 σ_T - Yield stress , [MPa]
 δ_5 - Specific elongation at fracture , [%]
 ψ - Reduction of area , [%]
KCU - Impact strength , [kJ / m²]
HB - Brinell hardness , [MPa]

Physical properties :

- T** - Test temperature , [Grade]
E - Young modulus , [MPa]
 α - Coefficient of linear expansion (range 20° - T) , [1/Grade]
 λ - Thermal (heat) condition coefficient , [Watt/(m·Grade)]
 ρ - Density , [kg/m³]
C - Specific heat (range 20° - T), [J/(kg·Grade)]
R - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
 Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

