

Database of Steel and Alloy (Marochnik)

splav.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [High-temperature or heat-resistant steel and alloy](#)

Characteristics for grade KHN75MBTYU (XH75MБTЮ).

Grade :	KHN75MBTYU (XH75MБTЮ) (ЭИ602)
Classification :	High-temperature or heat-resistant alloy
Equivalent grades:	Is absent

Chemical composition in % for grade KHN75MBTYU (XH75MБTЮ)

Fe	C	Si	Mn	Ni	S	P	Cr	Mo	Nb	Ti	Al
max 3	max 0.1	max 0.8	max 0.4	68.568 - 77.6	max 0.012	max 0.02	19 - 22	1.8 - 2.3	0.9 - 1.3	0.35 - 0.75	0.35 - 0.75

Mechanical properties under T=20°C for grade KHN75MBTYU (XH75MБTЮ)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Sheet, GOST 24982-81			900-930		40			Guenching 1050 - 1080°C,
Casting, GOST 7769-82			860	400	43	37		Guenching 1050 - 1080°C, air,

Technological properties for grade KHN75MBTYU (XH75MБTЮ)

Weldability:	without limitations.
--------------	----------------------

Physical properties for grade KHN75MBTYU (XH75MБTЮ)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20	1.9			8300		
100		12.4	13.45			
200		13.4	15.3			
300		14.2	16.7			
400	1.65	15	18.5			
500	1.63	15.8	20.2			
600	1.5	16.5	22.3			
700	1.37	18.1	24.4			
T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹

Specification : Mechanical properties :

- σ_B - Tensile strength , [MPa]
 σ_T - Yield stress , [MPa]
 δ_5 - Specific elongation at fracture , [%]
 ψ - Reduction of area , [%]

- KCU** - Impact strength , [kJ / m²]
HB - Brinell hardness , [MPa]

Physical properties :

- T** - Test temperature , [Grade]
E - Young modulus , [MPa]
 α - Coefficient of linear expansion (range 20° - T) , [1/Grade]
 λ - Thermal (heat) condition coefficient , [Watt/(m·Grade)]
 ρ - Density , [kg/m³]
C - Specific heat (range 20° - T) , [J/(kg·Grade)]
R - Electrical resistance , [Ohm·m]

Weldability :

- without limitations** - welding is done without heating and subsequent heat treating
limited weldability - welding is possible under heating up to 100-120 grade and subsequent heat treating
hard weldability - obtaining the quality welding needs the additional operations: heating up to 200-300 grade; the heat treating is annealing

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more than 2500 steels and alloys (stainless steel, alloy steel, carbon steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
 Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

