

# Database of Steel and Alloy (Marochnik)

[splat.kharkov.com/en](http://splat.kharkov.com/en)

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Nickel](#)

## Characteristics for grade NP2 ( НП2 ).

|                           |                         |
|---------------------------|-------------------------|
| <b>Grade :</b>            | NP2 ( НП2 )             |
| <b>Classification :</b>   | Semis nickel            |
| <b>Equivalent grades:</b> | <a href="#">Go here</a> |

## Chemical composition in % for grade NP2 ( НП2 )

| Ni+Co       | Fe         | C          | Si          | Mn          | S            | P            | Cu         | As           | Pb           | Mg         | Zn           | Sb           | Bi           | Sn           | Cd           | Impurity |
|-------------|------------|------------|-------------|-------------|--------------|--------------|------------|--------------|--------------|------------|--------------|--------------|--------------|--------------|--------------|----------|
| min<br>99.5 | max<br>0.1 | max<br>0.1 | max<br>0.15 | max<br>0.05 | max<br>0.005 | max<br>0.002 | max<br>0.1 | max<br>0.002 | max<br>0.002 | max<br>0.1 | max<br>0.007 | max<br>0.002 | max<br>0.002 | max<br>0.002 | max<br>0.002 | all 0.5  |

## Mechanical properties under T=20°C for grade NP2 ( НП2 )

| Assortment                    | Dimension | Direct. | $\sigma_B$ | $\sigma_T$ | $\delta_5$ | $\psi$ | KCU                 | Heat treatment |
|-------------------------------|-----------|---------|------------|------------|------------|--------|---------------------|----------------|
| -                             | mm        | -       | MPa        | MPa        | %          | %      | kJ / m <sup>2</sup> | -              |
| Sheet hotrolled, GOST 6235-91 |           |         | 370        |            | 15         |        |                     |                |
| Sheet, GOST 6235-91           |           |         | 370        |            | 35         |        |                     |                |
| Sheet, GOST 6235-91           |           |         | 540        |            | 2          |        |                     |                |
| Bar hotrolled, GOST 13083-77  |           |         | 440        |            | 10         |        |                     |                |
| Bar, GOST 13083-77            |           |         | 370        |            | 30         |        |                     |                |
| Bar, GOST 13083-77            |           |         | 540        |            | 5          |        |                     |                |
| Band, GOST 2170-73            |           |         | 390        |            | 35         |        |                     |                |
| Band, GOST 2170-73            |           |         | 540        |            | 3          |        |                     |                |

## Technological properties of the material NP2 ( НП2 ).

|                                |                |
|--------------------------------|----------------|
| <b>Melting temperature :</b>   | 1455 °C        |
| <b>Forging temperature :</b>   | 1140 - 1250 °C |
| <b>Annealing temperature :</b> | 700 - 800 °C   |
| <b>Casting temperature :</b>   | 1550 - 1650 °C |
| <b>Linear shrinkage :</b>      | 1 %            |

## Equivalent steels for grade NP2 ( НП2 )

Warning! Indicated both exact and nearest equivalents.

|         |
|---------|
| Germany |
|---------|

DIN, WNr

2.4060

Ni99.6

**Specification :****Mechanical properties :**

|            |                                             |
|------------|---------------------------------------------|
| $\sigma_B$ | - Tensile strength , [MPa]                  |
| $\sigma_T$ | - Yield stress , [MPa]                      |
| $\delta_5$ | - Specific elongation at fracture , [ % ]   |
| $\psi$     | - Reduction of area , [ % ]                 |
| <b>KCU</b> | - Impact strength , [ kJ / m <sup>2</sup> ] |
| <b>HB</b>  | - Brinell hardness , [MPa]                  |

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).  
 Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

