

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Precision alloy](#)

Characteristics for grade 64N (64H).

Grade :	64N (64H) (65H)
Classification :	Magnetically soft precision alloy
Equivalent grades:	Is absent

Chemical composition in % for grade 64N (64H)

Fe	C	Si	Mn	Ni	S	P
34.03 - 36.54	0.01 - 0.03	0.15 - 0.3	0.3 - 0.6	63 - 65	max 0.02	max 0.02

Mechanical properties under T=20°C for grade 64N (64H)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Band, GOST 10160-75			540	145	40			
Band cold-worked , GOST 10160-75			880		3	10		

Brinell hardness for 64N (64H) , Band GOST 10160-75	HB 10 ⁻¹ = 130 MPa
Brinell hardness for 64N (64H) , Band GOST 10160-75	HB 10 ⁻¹ = 200 MPa

Physical properties for grade 64N (64H)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20	1.9			8350		200
100		11.8				

Specification :

Mechanical properties :

- σ_B - Tensile strength , [MPa]
- σ_T - Yield stress , [MPa]
- δ_5 - Specific elongation at fracture , [%]
- ψ - Reduction of area , [%]
- KCU** - Impact strength , [kJ / m²]
- HB** - Brinell hardness , [MPa]

Physical properties :

- T** - Test temperature , [Grade]
E - Young modulus , [MPa]
 α - Coefficient of linear expansion (range 20° - T) , [1/Grade]
 λ - Thermal (heat) condition coefficient , [Watt/(m·Grade)]
 ρ - Density , [kg/m³]
C - Specific heat (range 20° - T), [J/(kg·Grade)]
R - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
 Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

