

# Database of Steel and Alloy ( Marochnik )

[splav.kharkov.com/en](http://splav.kharkov.com/en)

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Steel for special use](#)

## Characteristics for grade 76T ( 76T ).

|                           |                          |
|---------------------------|--------------------------|
| <b>Grade :</b>            | 76T ( 76T )              |
| <b>Classification :</b>   | Steel for rail transport |
| <b>Equivalent grades:</b> | Is absent                |

## Chemical composition in % for grade 76T ( 76T )

| C           | Si          | Mn          | S         | P         | Ti            |
|-------------|-------------|-------------|-----------|-----------|---------------|
| 0.71 - 0.84 | 0.18 - 0.55 | 0.75 - 1.25 | max 0.045 | max 0.035 | 0.004 - 0.025 |

## Mechanical properties under T=20°C for grade 76T ( 76T )

| Assortment           | Dimension | Direct. | $\sigma_B$ | $\sigma_T$ | $\delta_5$ | $\psi$ | KCU                 | Heat treatment |
|----------------------|-----------|---------|------------|------------|------------|--------|---------------------|----------------|
| -                    | mm        | -       | MPa        | MPa        | %          | %      | kJ / m <sup>2</sup> | -              |
| Steel, GOST 51045-97 |           |         | 780-1080   |            | 3-5        |        | 150                 |                |

|                                                        |                                     |
|--------------------------------------------------------|-------------------------------------|
| Brinell hardness for 76T ( 76T ) , Steel GOST 51045-97 | HB 10 <sup>-1</sup> = 302 - 420 MPa |
|--------------------------------------------------------|-------------------------------------|

## Physical properties for grade 76T ( 76T )

| T     | E 10 <sup>-5</sup> | $\alpha$ 10 <sup>6</sup> | $\lambda$      | $\rho$            | C            | R 10 <sup>9</sup> |
|-------|--------------------|--------------------------|----------------|-------------------|--------------|-------------------|
| Grade | MPa                | 1/Grade                  | Watt/(m·Grade) | kg/m <sup>3</sup> | J/(kg·Grade) | Ohm·m             |
| 20    |                    |                          |                | 7850              |              |                   |

### Specification : Mechanical properties :

- $\sigma_B$  - Tensile strength , [MPa]
- $\sigma_T$  - Yield stress, [MPa]
- $\delta_5$  - Specific elongation at fracture , [ % ]
- $\psi$  - Reduction of area , [ % ]
- KCU - Impact strength , [ kJ / m<sup>2</sup>]
- HB - Brinell hardness , [MPa]

### Physical properties :

- T - Test temperature , [Grade]
- E - Young modulus , [MPa]
- $\alpha$  - Coefficient of linear expansion (range 20° - T ) , [1/Grade]
- $\lambda$  - Termal (heat) condition coefficient , [Watt/(m·Grade)]
- $\rho$  - Density , [kg/m<sup>3</sup>]
- C - Specific heat ( range 20° - T ), [J/(kg·Grade)]
- R - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys

(stainless steel, alloy steel, carbone steel, structural steel, tool steel,  
cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).  
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

