

Database of Steel and Alloy (Marochnik)

splav.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Steel for special use](#)

Characteristics for grade S345T (C345T).

Grade :	S345T (C345T)
Classification :	Steel for structural constructions
Equivalent grades:	Is absent

Chemical composition in % for grade S345T (C345T)

C	Si	Mn	Ni	S	P	Cr	N	Cu
max 0.22	0.05 - 0.15	0.8 - 1.1	max 0.3	max 0.05	max 0.04	max 0.3	max 0.012	max 0.3

Technological properties for grade S345T (C345T)

Weldability:	without limitations.
---------------------	----------------------

Specification :

Weldability :

- without limitations** - welding is done without heating and subsequent heat treating
- limited weldability** - welding is possible under heating up to 100-120 grade and subsequent heat treating
- hard weldability** - obtaining the quality welding needs the additional operations: heating up to 200-300 grade; the heat treating is annealing

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more than 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

