

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Structural steel](#)

Characteristics for grade 20N2M (20H2M).

Grade :	20N2M (20H2M) (20HM)
Classification :	Alloy structural steel
Equivalent grades:	Go here

Chemical composition in % for grade 20N2M (20H2M)

C	Si	Mn	Ni	S	P	Cr	Mo	Cu
0.17 - 0.25	0.17 - 0.37	0.4 - 0.7	1.5 - 1.9	max 0.035	max 0.035	max 0.3	0.2 - 0.3	max 0.3

Mechanical properties under T=20°C for grade 20N2M (20H2M)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Bar, GOST 4543-71	Ø 15		880	685	10	50	780	Guenching 860°C, oil, Drawing 180°C, air,

Equivalent steels for grade 20N2M (20H2M)

Warning! Indicated both exact and nearest equivalents.

USA
-
4620 4620H G46200 H46200

Specification :

Mechanical properties :

σ_B	- Tensile strength , [MPa]
σ_T	- Yield stress , [MPa]
δ_5	- Specific elongation at fracture , [%]
ψ	- Reduction of area , [%]
KCU	- Impact strength , [kJ / m ²]
HB	- Brinell hardness , [MPa]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more than 2500 steels and alloys (stainless steel, alloy steel, carbene steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

