

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Structural steel](#)

Characteristics for grade 20KHNR (20XHP).

Grade :	20KHNR (20XHP)
Substitute:	20XH
Classification :	Alloy structural steel
Equivalent grades:	Is absent

Chemical composition in % for grade 20KHNR (20XHP)

C	Si	Mn	Ni	S	P	Cr	Ti	Cu	B
0.16 - 0.23	0.17 - 0.37	0.6 - 0.9	0.8 - 1.1	max 0.035	max 0.035	0.7 - 1.1	max 0.06	max 0.3	0.001 - 0.005

Temperature of critical points for grade 20KHNR (20XHP).

$A_{c1} = 740$, $A_{c3}(A_{cm}) = 830$, $A_{r3}(A_{rcm}) = 725$, $A_{r1} = 650$

Mechanical properties under T=20°C for grade 20KHNR (20XHP)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Bar	Ø 25		1420	1370	14	60	1080	Normalizing 930°C, air, Guenching 840°C, oil, Drawing 200°C, air,
Bar	Ø 75		1060	970	15	60	1080	Normalizing 930°C, air, Guenching 840°C, oil, Drawing 200°C, air,
Bar, GOST 4543-71	Ø 15		1180	980	10	50	880	Guenching and drawing

Brinell hardness for 20KHNR (20XHP) , Rolled stock GOST 4543-71

HB 10⁻¹ = -1 MPa

Technological properties for grade 20KHNR (20XHP)

Weldability:	limited weldability.
Flakes :	predisposed
Temper brittleness:	predisposed

Specification :
Mechanical properties :

σ_B	- Tensile strength , [MPa]
σ_T	- Yield stress , [MPa]
δ_5	- Specific elongation at fracture , [%]
ψ	- Reduction of area , [%]
KCU	- Impact strength , [kJ / m ²]
HB	- Brinell hardness , [MPa]

Weldability :

without limitations	- welding is done without heating and subsequent heat treating
limited weldability	- welding is possible under heating up to 100-120 grade and subsequent heat treating
hard weldability	- obtaining the quality welding needs the additional operations: heating up to 200-300 grade; the heat treating is annealing

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more than 2500 steels and alloys (stainless steel, alloy steel, carbon steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpful for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

