

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Titanium](#)

Characteristics for grade VT9 (BT9).

Grade :	VT9 (BT9)
Classification :	Titanium wrought alloy
Equivalent grades:	Is absent

Chemical composition in % for grade VT9 (BT9)

Fe	C	Si	Mo	N	Ti	Al	Zr	O	H	Impurity
max 0.25	max 0.1	0.2 - 0.35	2.8 - 3.8	max 0.05	86.15 - 89.9	5.8 - 7	1 - 2	max 0.15	max 0.015	other 0.3

Comment: Ti is a basis; the percentage of Ti is given approximately.

Mechanical properties under T=20°C for grade VT9 (BT9)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Bar, GOST 26492-85			930-980		6-7	15-16	200-250	Annealing
Bar, GOST 26492-85			980-1230		7-9	16-30	300	Annealing
Die			1100-1300		8-14	25-45	200-500	Annealing

Physical properties for grade VT9 (BT9)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20	1.18			4510		

Specification :

Mechanical properties :

- σ_B - Tensile strength , [MPa]
- σ_T - Yield stress , [MPa]
- δ_5 - Specific elongation at fracture , [%]
- ψ - Reduction of area , [%]
- KCU - Impact strength , [kJ / m²]
- HB - Brinell hardness , [MPa]

Physical properties :

- T - Test temperature , [Grade]
- E - Young modulus , [MPa]
- α - Coefficient of linear expansion (range 20° - T) , [1/Grade]

λ - Thermal (heat) condition coefficient , [Watt/(m·Grade)]

ρ - Density , [kg/m³]

C - Specific heat (range 20° - T), [J/(kg·Grade)]

R - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

