

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Tool steel](#)

Characteristics for grade 9KHFM (9XΦM).

Grade :	9KHFM (9XΦM)
Classification :	Alloy tool steel
Equivalent grades:	Is absent

Chemical composition in % for grade 9KHFM (9XΦM)

C	Si	Mn	Ni	S	P	Cr	Mo	W	Cu
0.8 - 0.9	0.1 - 0.4	0.3 - 0.6	max 0.4	max 0.03	max 0.03	0.4 - 0.7	0.15 - 0.25	0.15 - 0.3	max 0.3

Mechanical properties under T=20°C for grade 9KHFM (9XΦM)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Band annealed , GOST 2283-79	0.1 - 4		930					

Specification :

Mechanical properties :

- σ_B - Tensile strength , [MPa]
- σ_T - Yield stress , [MPa]
- δ_5 - Specific elongation at fracture , [%]
- ψ - Reduction of area , [%]
- KCU** - Impact strength , [kJ / m²]
- HB** - Brinell hardness , [MPa]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

