

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Tool steel](#)

Characteristics for grade U11 (Y11).

Grade :	U11 (Y11)
Classification :	Carbon tool steel
Equivalent grades:	Go here

Chemical composition in % for grade U11 (Y11)

C	Si	Mn	Ni	S	P	Cr	Cu
1.06 - 1.13	0.17 - 0.33	0.17 - 0.33	max 0.25	max 0.028	max 0.03	max 0.2	max 0.25

Temperature of critical points for grade U11 (Y11).

$Ac_1 = 730$, $Ac_3(Ac_m) = 810$, $Ar_1 = 700$, $Mn = 200$

Mechanical properties under T=20°C for grade U11 (Y11)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Band annealed	0.08 - 3		750		10			

Brinell hardness for U11 (Y11) (annealing) ,	HB 10⁻¹ = 207 MPa
---	-------------------------------------

Physical properties for grade U11 (Y11)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20				7810		

Equivalent steels for grade U11 (Y11)

Warning! Indicated both exact and nearest equivalents.

USA	Germany	Japan	France	England	Italy	Spain	Sweden	Bulgaria	Hungary	Poland	Romania	Austria
-	DIN,WNr	JIS	AFNOR	BS	UNI	UNE	SS	BDS	MSZ	PN	STAS	ONORM
G51320 T72301 T72305 W1-10 W5	1.1654 C105W1 C105W2 C110W	SK3	C105E2U Y1-105	BW1B	C100KU	C102	1880	U11	S111 S112	N10 N10E N11 N11E	OSC11	BOHLERK990

Specification :**Mechanical properties :**

σ_B	- Tensile strength , [MPa]
σ_T	- Yield stress , [MPa]
δ_5	- Specific elongation at fracture , [%]
ψ	- Reduction of area , [%]
KCU	- Impact strength , [kJ / m ²]
HB	- Brinell hardness , [MPa]

Physical properties :

T	- Test temperature , [Grade]
E	- Young modulus , [MPa]
α	- Coefficient of linear expansion (range 20° - T) , [1/Grade]
λ	- Thermal (heat) condition coefficient , [Watt/(m·Grade)]
ρ	- Density , [kg/m ³]
C	- Specific heat (range 20° - T) , [J/(kg·Grade)]
R	- Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

