

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Tool steel](#)

Characteristics for grade 75KHM (75XM).

Grade :	75KHM (75XM)
Substitute:	9X2
Classification :	Tool steel for roller
Equivalent grades:	Is absent

Chemical composition in % for grade 75KHM (75XM)

C	Si	Mn	Ni	S	P	Cr	Mo
0.7 - 0.8	0.2 - 0.6	0.2 - 0.7	max 0.5	max 0.03	max 0.03	1.4 - 1.7	0.2 - 0.3

Mechanical properties under T=20°C for grade 75KHM (75XM)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Steel	500	longitudinal	750	430	19	41	240	Double normalizing and drawing

Technological properties for grade 75KHM (75XM)

Weldability:	is not used.
Flakes :	weakly predisposed
Temper brittleness:	not predisposed

Physical properties for grade 75KHM (75XM)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20				7900		
100			45		490	
200			41		500	
300			40		530	
400			39		570	
500			38		640	
600			37		750	
700			35		900	
800					700	

900					760	
1000					810	
T	$E \cdot 10^{-5}$	$\alpha \cdot 10^6$	λ	ρ	C	$R \cdot 10^9$

Specification :**Mechanical properties :**

- σ_B - Tensile strength , [MPa]
 σ_T - Yield stress , [MPa]
 δ_5 - Specific elongation at fracture , [%]
 ψ - Reduction of area , [%]
KCU - Impact strength , [kJ / m²]
HB - Brinell hardness , [MPa]

Physical properties :

- T** - Test temperature , [Grade]
E - Young modulus , [MPa]
 α - Coefficient of linear expansion (range 20° - T) , [1/Grade]
 λ - Thermal (heat) condition coefficient , [Watt/(m·Grade)]
 ρ - Density , [kg/m³]
C - Specific heat (range 20° - T) , [J/(kg·Grade)]
R - Electrical resistance , [Ohm·m]

Weldability :

- without limitations** - welding is done without heating and subsequent heat treating
limited weldability - welding is possible under heating up to 100-120 grade and subsequent heat treating
hard weldability - obtaining the quality welding needs the additional operations: heating up to 200-300 grade; the heat treating is annealing

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more than 2500 steels and alloys (stainless steel, alloy steel, carbide steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
 Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

