



World leaders in the conservation of man-made resources and the environment

PRODUCT SPECIFICATION SHEET **BELZONA® 1141**

1. PRODUCT NAME

Belzona® 1141

(Conductive Metal)

An electrically conductive metal repair and bonding system.

2. MANUFACTURER

Belzona Inc.,

2000 N.W. 88th Court
Miami, Florida 33172

Belzona Polymerics Ltd.,

Claro Road, Harrogate,
HG1 4AY, England.

3. PRODUCT DESCRIPTION

A two component paste grade system based on a blend of electrically conductive fillers and high molecular weight reactive polymers and oligomers. When cured, the material is durable, fully machinable and electrically conductive.

Applications

Bonding continuity straps
Non-magnetic repairs.
Sealing anode clamps.
Bonding test leads.
Cosmetic repair to bronze castings.
Conductive irregular shims.

4. TECHNICAL DATA

Base Component

Appearance	Paste
Color	Copper
Density	1.90 - 1.94

Solidifier Component

Appearance	Paste
Color	Black
Density	1.42 - 1.46

Mixed Properties

Mixing Ratio by Weight (Base : Solidifier)	4.3 : 1
Mixing Ratio by Volume (Base : Solidifier)	3 : 1
Mixed Form	Paste
Slump nil at	0.5 inch (1.27 cm)
Mixed Density	1.80

• **Shelf Life:**

Separate base and solidifier components shall have a 5 year shelf life when stored between 32°F (0°C) and 86°F (30°C).

• **Working Life:**

Will vary according to temperature.
At 77°F (25°C) the usable life of mixed material is 25 minutes.

• **Volume Capacity:**

The volume capacity of a 1.5 kg. unit of mixed **Belzona® 1141** is 51 cu.in. (833 cm³).

• **Cure Time:**

Will be reduced for thicker sections and extended for thinner applications. At a thickness of approximately 1/4 in. (6 mm), allow to solidify for the times shown in the chart below before subjecting it to the conditions indicated.

5. PHYSICAL / MECHANICAL PROPERTIES

Determined after 7 days cure at 77°F (25°C). Post curing the material with heat results in a more highly cross-linked polymer. For enhanced performance this material may be post-cured by heating to 212°F (100°C) for a period of up to 24 hours.

• **Adhesion:**

Tensile Shear

When tested in accordance with ASTM D1002, using degreased mild steel, grit blasted to a 3 mil (75 microns) profile, typical values will be 1600 psi (112 kgs/cm²).

• **Chemical Resistance:**

Once fully cured, the material will demonstrate excellent resistance to the following chemicals;

- 20% ammonia solution
- lime water
- 20% potassium hydroxide
- 20% sodium hydroxide
- propanol
- butanol
- ethylene glycol
- diethanolamine
- methylamine (25% in water)
- hydrocarbons
- mineral oils
- inorganic salts

• **Compressive Strength:**

When tested in accordance with ASTM D695, typical values obtained will be 11,500 psi (809 kgs/cm²).

• **Corrosion Resistance:**

Once fully cured, will show no visible signs of corrosion after 5,000 hours exposure in the ASTM B117-73 salt spray cabinet.

• **Current Carrying Capacity:**

The fully cured material will be capable of carrying a maximum of 6A/cm² and up to 3A/cm² continuously.

CURE TIMES

TEMPERATURE	50°F (10°C)	59°F (15°C)	68°F (20°C)	77°F (25°C)	86°F (30°C)
Movement or use involving no loading or immersion	10 hrs	5 hrs	2½ hrs	2 hrs	1 hr
Machining and/or light loading	24 hrs	12 hrs	4 hrs	3 hrs	2½ hrs
Full electrical, mechanical or thermal loading	3 days	2 days	1 day	16 hrs	12 hrs
Immersion in chemicals	12 days	7 days	4 days	20½ days	1½ days

• **Hardness:**

The hardness of the material when tested to ASTM D2240 after 7 days cure at 77°F (25°C) is typically 85 Shore D.

• **Heat Resistance:**

For many typical applications, the product is thermally stable to 392°F (200°C) dry and 200°F (93°C) wet.

• **Heat Distortion Temperature:**

Tested to ASTM D648 (264 psi fiber stress), typical values obtained will be 136°F (58°C).

• **Specific Resistance:**

At 68°F (20°C) in air, and with current of 1 amp specific resistance will typically be 8.05 x 10⁻³ ohm.cm.

6. SURFACE PREPARATION AND APPLICATION PROCEDURES

For proper technique, refer to the Belzona® Instructions for Use leaflet which is enclosed with each packaged product.

7. AVAILABILITY AND COST

Belzona® 1141 is available from a network of Belzona® Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona® Distributor in your area.

8. WARRANTY

Belzona® guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona® Instructions for Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

9. TECHNICAL SERVICES

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

10. HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

Belzona Polymerics Ltd.,
Claro Road,
Harrogate, HG1 4AY,
England.
Tel: +44 (0) 1423 567641
Fax: +44 (0) 1423 505967
E-Mail: belzona@belzona.co.uk

Belzona Inc.,
2000 N.W. 88 Court,
Miami, Florida 33172,
U.S.A.
Tel: +1 (305) 594 4994
Fax: +1 (305) 599 1140
E-Mail: belzona@belzona.com



BS EN ISO 9002 : 1994
Certificate No. Q/09335



www.belzona.com

Copyright © 2003 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 1996-2001 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher.

Belzona® is a registered trademark

Printed in England 4/03 UK

Private and Confidential - For Internal Use Only



Belzona® 1141 - Product Specification Sheet (2)