



World leaders in the conservation of man-made resources and the environment

PRODUCT SPECIFICATION SHEET BELZONA® 1341NSF

1. PRODUCT NAME

Belzona® 1341NSF (Supermetalgilde)

A drinking water approved coating system for improving the efficiency of fluid handling systems and protecting metals from the effects of erosion-corrosion.



Certified to
ANSI/NSF 61

2. MANUFACTURER

Belzona Polymeric Ltd.,
Claro Road, Harrogate,
HG1 4AY, England.

Belzona Inc.,
2000 N.W. 88 Court,
Miami, Florida 33172, U.S.A.

3. PRODUCT DESCRIPTION

A two component system specifically designed to improve the efficiency of fluid handling equipment and to protect all metals from the effects of erosion-corrosion.

Applications

Pumps
Heat exchangers
Water boxes
Valves
Water tanks
Pipes
Tube sheets

4. TECHNICAL DATA

Base component

Appearance	Thixotropic paste
Color	Gray or Blue
Density	1.58-1.63 g/cm ³

Solidifier component

Appearance	Clear liquid
Color	Clear
Density	1.17-1.19 g/cm ³

Mixed properties

Mixing ratio by weight	2 : 1
Mixing ratio by volume	3 : 2
Density	1.42-1.46 g/cm ³

• **Limitations of Use**

Belzona® 1341NSF should not be used at temperatures below 50°F (10°C). Where material has been stored below this temperature, warm the Base and Solidifier units until they attain a temperature of 68-77°F (20-25°C).

• **Shelf life**

Separate Base and Solidifier components shall have a shelf life of at least 3 years when stored between 32°F (0°C) and 86°F (30°C).

• **Working life**

Will vary according to temperature:

Temperature	Working life
50°F (10°C)	70 minutes
59°F (15°C)	50 minutes
68°F (20°C)	35 minutes
77°F (25°C)	25 minutes
86°F (30°C)	16 minutes

• **Coverage rate**

To achieve the correct film thickness of 10 mils (250 microns), a practical coverage rate of 19.5 sq. ft (1.8 sq. m) per 750g unit should be obtained or 130 sq. ft (12 sq. m) per 5kg.

• **Volume capacity**

The volume capacity of mixed Belzona® 1341NSF is 31.73 in³ / 750g or 212 in.³ (3.475 litres) / 5kg.

• **Cure time**

At a thickness of approximately ¼ in. (6 mm) allow to cure for the times shown in the chart below before subjecting it to the conditions indicated.

5. PHYSICAL/MECHANICAL PROPERTIES

Determined after 7 days cure at 68°F (20°C).

• **Abrasion resistance**

Taber

The sliding abrasion resistance using Taber Abraser using H10/CS17 wheels and 1kg load is typically:

Wet	52 mm ³
Dry	6 mm ³

Loss per 1000 cycles.

• **Adhesion**

Tensile shear

When tested in accordance with ASTM D1002 using degreased strips, grit blasted to a 3-4mil (75 micron) profile, typical values obtained will be:

20°C cure	
Mild steel	2,500 psi (175 kg/cm ²)
Stainless steel	2,780 psi (195 kg/cm ²)
Copper	2,230 psi (156 kg/cm ²)
Aluminum	1,570 psi (110 kg/cm ²)

100°C cure

Mild steel	3,250 psi (228 kg/cm ²)
------------	-------------------------------------

• **Cathodic disbondment**

When tested in accordance with ASTM G8 typical values obtained will be Class B.

• **Cavitation resistance**

When tested to a modified version of ASTM G32 using stationary specimens at 20KHz frequency and 50 microns amplitude a typical volume loss will be 12 mm³/hour.

• **Chemical resistance**

Once fully cured, the material will demonstrate excellent resistance to the following chemicals:

Water
Sea water
Inorganic salt solutions
10% sodium hydroxide

CURE TIMES

TEMPERATURE	50°F (10°C)	59°F (15°C)	68°F (20°C)	77°F (25°C)	86°F (30°C)
Movement or use involving no loading	24 hours	12 hours	8 hours	7 hours	6 hours
Movement or use involving light loading	48 hours	24 hours	16 hours	14 hours	12 hours
Full mechanical/thermal loading or water immersion	14 days	7 days	3 days	2½ days	2 days
Immersion in chemicals	21 days	10 days	7 days	6 days	5 days

• Compressive yield strength

When tested in accordance with ASTM D695 typical values obtained will be:
68°F (20°C) cure 6,900 psi (485 kg/cm²)
212°F (100°C) cure 8,500 psi (598 kg/cm²)

• Flexural strength

When tested in accordance with ASTM D790 typical values obtained will be:
68°F (20°C) cure 5,900 psi (415 kg/cm²)
212°F (100°C) cure 6,400 psi (450 kg/cm²)

• Heat distortion temperature

When tested in accordance with ASTM D648 typical values obtained will be:
68°F (20°C) cure 111°F (44°C)
212°F (100°C) cure 156°F (69°C)

• Heat resistance

For many typical applications the material is suitable for continuous immersion in aqueous solutions up to 140°F (60°C). The material will be stable under dry conditions up to 392°F (200°C) and down to -40°F (-40°C).

• Impact strength

When tested in accordance with ASTM D256 typical values obtained will be:
68°F (20°C) cure 1 ft.lb./in (54 J/m)
212°F (100°C) cure 1.15 ft.lb./in (62 J/m)

• Potable Water Approval

Belzona® 1341 bearing the NSF mark is approved for contact with drinking water subject to the following restrictions.
For use on distribution line pumps of >4 inch diameter with a minimum daily output of 4800 gallons/ft² of coated pump surface
For use on tanks of > 100,000 gallons

• Pump Efficiency Enhancement

The **Belzona® 1341NSF** system has been shown to be capable of bringing about an increase in pump efficiency of up to 7% in Independent tests carried out by the National Engineering Laboratory, East Kilbride, Glasgow, Scotland, test number 0230 432/88 BEM/01 and the Aurora Pump Company, North Aurora, Illinois, test number 0789089/1089037.

• Thermal expansion

When tested in accordance with ASTM E228 typical values obtained will be:
74.7 ppm/°C

6. SURFACE PREPARATION AND APPLICATION PROCEDURES

For proper technique, refer to the Belzona Instructions For Use leaflet which is enclosed with each packaged product.

7. AVAILABILITY AND COST

Belzona® 1341NSF is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

8. WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Instructions For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

9. TECHNICAL SERVICES

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

10. HEALTH AND SAFETY

Prior to using this material, please consult the Material Safety Data Sheet provided with each packaged product

11. APPROVALS/ACCEPTANCES

NSF
U.S.D.A.
INGERSOL RAND
SULZER PUMPS
SPP LTD.
SSW PUMP SERVICES
AURORA PUMPS

Belzona Polymerics Ltd.,
Claro Road,
Harrogate, HG1 4AY,
England.
Tel: +44 (0) 1423 567641
Fax: +44 (0) 1423 505967
E-Mail: belzona@belzona.co.uk



BS EN ISO 9002 : 1994
Certificate No. Q/09335



www.belzona.com

Belzona Inc.,
2000 N.W. 88 Court,
Miami, Florida 33172,
U.S.A.
Tel: +1 (305) 594 4994
Fax: +1 (305) 599 1140
E-Mail: belzona@belzona.com

Copyright © 2003 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 1999-2002 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher.

Belzona® is a registered trademark

Printed in England 4/03 UK

Private and Confidential - For Internal Use Only



Belzona®1341NSF - Product Specification Sheet (2)