



BELZONA® 3912

INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

Apply **ONLY** to structurally sound surfaces.

- Remove mineral chippings of ¼ inch (6 mm) or more and sweep the area clean before proceeding to (b).
- All surfaces should be made clean, dry and firm. Treat substrates where moss, lichens and vegetation have been removed with a fungicidal wash (e.g. Nuodex or similar) applied to the manufacturers' instructions to kill off residual spores.

2. APPLYING BELZONA® 3912

Belzona® 3912 should only be applied to porous or bituminous substrates (excluding asphalt).

FOR BEST RESULTS

Do not apply when:-

- There is a risk of rain, snow fog or frost.
- Surface temperature is 41°F (5°C) and falling, or relative humidity rises above 80%.
- A combination of high relative humidity and low temperature occurs.
- Any of the above conditions is likely to occur within 45 minutes.

Brush **Belzona® 3912** well into the surface, not exceeding the recommended coverage rate. Allow the minimum overcoating times to elapse before overcoating with **Belzona® 3111**. Do not leave for more than 2 days before applying **Belzona® 3111**. Should this time be exceeded, a further application of **Belzona® 3912** must be carried out prior to application of **Belzona® 3111**.

NOTE: THINNING

Under extremely warm or windy conditions it may be necessary to thin **Belzona® 3912** by up to a maximum of 5% by volume, with clean water. Standard coverage rates apply, regardless of whether or not thinning takes place.

3. TECHNICAL DATA

MINIMUM OVERCOATING TIMES:

Temperature	10°C	20°C	30°C
Overcoat with Belzona® 3111 after	4 hrs	2 hrs	1 hr

MAXIMUM OVERCOATING TIME: 2 days

COVERAGE RATES:

Substrate	Coverage Rate per litre	
New Asbestos Cement	86.1 sq.ft.	(8.0 m ²)
Old Asbestos Cement	43.0 sq.ft.	(4.0 m ²)
Wood	64.6 sq.ft.	(6.0 m ²)
Smooth Felt/Bitumen	64.6 sq.ft.	(6.0 m ²)
Mineral Felt/Small Chippings	38.7 sq.ft.	(3.6 m ²)
Concrete/Brick	41.9 sq.ft.	(3.9 m ²)
Breeze Block	21.5 sq.ft.	(2.0 m ²)
De-chipped Surfaces	21.5 sq.ft.	(2.0 m ²)

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the enclosed Material Safety Data Sheets.

All descriptions are based on the results of long term tests carried on in our laboratories and are believed to be true and accurate. No condition or warranty is given covering the results from the use of our products in any particular case, whether the purpose is disclosed or not, and we cannot accept liability if the desired results are not obtained.

Copyright © 1996 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 1993, 1995 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher.

Belzona® is a registered trademark

Belzona® 3912 - Instructions For Use (Page 2)

Belzona Polymerics Ltd.,
Claro Road,
Harrogate, HG1 4AY,
England.
Tel: +44 (0) 1423 567641
Fax: +44 (0) 1423 505967

Belzona Inc.,
2000 N.W. 88 Court,
Miami, Florida 33172,
U.S.A.
Tel: +1 (305) 594 4994
Fax: +1 (305) 599 1140



BS EN ISO 9002 : 1994
Certificate No. Q/09335



Printed in England Publication No. 45-10-96