



World leaders in the conservation of man-made resources and the environment

PRODUCT SPECIFICATION SHEET BELZONA® 6111

1. PRODUCT NAME

**Belzona® 6111
(Liquid Anode)**

2. MANUFACTURER

Belzona Inc.,
2000 NW 88th Court,
Miami, Florida 33172

Belzona Polymerics Ltd.,
Claro Road, Harrogate,
HG1 4AY, England.

3. PRODUCT DESCRIPTION

A two part zinc rich epoxy system providing corrosion protection to steel- work. The material is solvent based and can be brush or spray applied.

Applications.

All structural steelwork
Tanks
Pipes
Cooling Towers
Bridges

4. TECHNICAL DATA

Base Component:

Appearance	Viscous Liquid
Color	Gray
Odor	Solvent
Viscosity	7.8 - 10 Poise
Solids by weight	87.6%
Solids by volume	53.2%
Density	3.275 - 3.342g/cm ³
Flash Point	>73°F (23°C)

Solidifier Component

Appearance	Mobile liquid
Color	Blue or Amber
Odor	Solvent
Density	Blue 0.92 - 0.93 g/cm ³ Gray 0.905 - 0.915 g/cm ³
Solids by weight	31.8 %
Solids by volume	26.8 %
Flash point	> 73°F (23°C)

Mixed Components

Mixing Ratio by Volume (Base : Solidifier)	3.5 : 1
Density	2.62g/cm ³
Solids by weight	84%
Solids by volume	49%
wet film thickness	3 mils (76 microns)
dry film thickness	1½ mils (38 microns)
Appearance	Liquid
Color	Blue or gray
Odor	Solvent

• **Zinc Content:**

The zinc content of the applied dry film is not less than 90%.

• **VOC Content:**

	lbs/US gal	g/liter
Base	3.41	408
Solidifier 5.37	643	
Mixed	3.96	475

• **Shelf Life:**

Separate base and solidifier components will have a guaranteed minimum shelf life of 5 years when stored between 32°F (0°C) and 86°F (30°C).

• **Working Life:**

Once mixed the usable life will vary with temperature.
50°F (10°C) 72 hours
68°F (20°C) 48 hours
86°F (30°C) 24 hours

• **Coverage Rate:**

The average practical coverage rate for two coats at 1½ mils dry film thickness per coat (total 3 mils or 76 microns) is 19.4 sq.ft. (1.8 sq.m.) per kg.

• **Cure Time:**

Allow to solidify for the times shown in the chart below before subjecting it to the condition indicated.

5. PHYSICAL / MECHANICAL PROPERTIES

Determined after 7 days cure at 77°F (25°C)

• **Adhesion**

Cross Hatch

When tested in accordance with BS 3900 Part E6 a 100% pass is obtained.

Tensile Shear

When tested in accordance with ASTM D1002 the typical tensile shear adhesion obtained is 1150 psi (80 kgs/cm²).

• **Chemical Resistance:**

If the Belzona® 6111 system is likely to come into contact with aggressive chemicals, Belzona® 5111 (Ceramic Cladding) should be used to overcoat the Belzona® 6111. For further details contact your Local Belzona Technical Consultant.

• **Corrosion Resistance:**

BS 3900: Part F4 artificial sea water spray 3,000 hours exposure with no corrosion breakdown on the system.

BS 3900: Part F3 artificial weathering 60 weeks (equivalent to 20 years natural weathering) with no corrosion breakdown on the system.

• **Flexibility:**

Tested on a ½" diameter mandrel a pass is achieved with no cracking or flaking.

• **Heat Resistance:**

For many typical applications the material is suitable for use between -40°F (-40°C) and 140°F(60°C) Wet
450°F (200°C) Dry

• **Impact Resistance**

When tested in accordance with BS 3900 Part E3 a pass is obtained up to 1/20 inch (1.25 mm).

CURE TIMES

Temperature	Touch Dry	Overcoating Time		Full Cure
		Minimum	Maximum	
50°F (10°C)	17 min	32 hrs	7 days	10 days
68°F (20°C)	10 min	16 hrs	5 days	7 days
86°F (30°C)	3 min	8 hrs	3 days	5 days

6. SURFACE PREPARATION AND APPLICATION PROCEDURES

For proper technique, refer to Belzona® Instructions For Use Leaflet which is enclosed with each packaged product.

7. AVAILABILITY AND COST

Belzona® 6111 is available from a network of Belzona® Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona® Distributor in your area.

8. WARRANTY

Belzona® guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona® Instructions For Use leaflet. Belzona® further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, etc.). Since Belzona® has no control over the use of the product described herein, no warranty for any application can be given.

9. TECHNICAL SERVICES

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

10. HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

11. APPROVALS/ ACCEPTANCES

U.S.D.A.

Belzona Polymerics Ltd.,
Claro Road,
Harrogate, HG1 4AY,
England.
Tel: +44 (0) 1423 567641
Fax: +44 (0) 1423 505967
E-Mail: Belzona@belzona.co.uk



BS EN ISO 9002 : 1994
Certificate No. Q/09335



www.belzona.com

Belzona Inc.,
2000 N.W. 88 Court,
Miami, Florida 33172,
U.S.A.
Tel: +1 (305) 594 4994
Fax: +1 (305) 599 1140
E-Mail: Belzona@belzona.com

Copyright © 2002 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 2000 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher.

Belzona® is a registered trademark

Printed in England 01/02 UK

Private and Confidential - For Internal Use Only



Belzona® 6111 - Product Specification Sheet (2)